



TGS WALL & FLOOR GROUT

Total Grout System

Date: 05 July 2016

Fact Sheet No.: D56051S

YOUR SMART ADVANTAGES

- Flexible – use on wooden floors
- Superior adhesion to fully vitrified tiles
- Low water absorption for showers
- Suitable for under floor heating
- For grout joints between 1 to 12mm

USES

Evo-Stik Technik TGS Grout is a polymer modified cementitious grout for wall and floor tiles on most substrates. It is colour fast and has very good water resistance and is suitable for grout coverings exposed to high mechanical stresses including in wet areas. It can be used for joint widths from 1mm to 12mm and it is also suitable for indoor & outdoor use.

Evo-Stik Technik TGS Grout will dry to a hard, durable, shrink resistant and water-resistant finish, suitable for internal and external locations and is particularly recommended for application in challenging areas such as on tiles applied over timber ply-boards, heated sub-floors and installations where some minor vibration can be expected.

Evo-Stik Technik TGS Grout is available in 7 colours, across a range which includes White, Cream, Ivory, Grey, Beige, Brown & Black all having the same super-smooth applications properties & long term durability even in the most challenging environments

PRODUCT CHARACTERISTICS

Colour	White, Cream, Ivory, Grey, Beige, Brown & Black
Form	Powder
Specific Gravity	1.1 dry, 1.8 when mixed as directed
Composition	Portland cement blend
Product Code	30810432, 30810439, 30814052, 30810441, 30607670, 30810435, 30810443, 30814053, 30810445, 30810447, 30810449, 30606432
Storage/Shelf Life	Store for up to 12 months from date of manufacture in original, unopened packaging under cool, dry, conditions within the temperature range of +5°C to

+30°C and out of direct sunlight. Protect from frost.

TYPICAL PERFORMANCE DATA (Approx.)

Application Temperature	+5°C to +30°C
Service Temperature	-15°C to +70°C
Coverage	Coverage is dependent on the tile dimensions and joint width. It can be calculated using the formula below: $\frac{(L + B) \times W \times D \times 1.8}{(L \times B)} = \text{kg/m}^2$ <p>Length of tile in mm; B – Breadth of tile in mm; W – Width of joint in mm; D – Depth of joint in mm; 1.6 – Specific Gravity</p>
Drying Times	Open time is 1 hour and final set after 24 hours
Solvent for Cleaning Up	Water

DIRECTIONS FOR USE

IMPORTANT: Before using Evo-Stik Technik TGS Grout refer to the relevant Health & Safety Data Sheet, available at www.bostik.co.uk.

PREPARATION

1. Ensure that tiles are firmly fixed and adhesive is completely set. Bostik adhesives should normally be left for at least 24 hours before grouting.
2. Ensure tiles and joints are clean, dry, sound and free from dust, grease or any contamination.
3. Some tiles have a soft surface which may be scratched during grouting and tiles with a matt or porous texture may be prone to staining. You are advised to test the grout on a spare tile for suitability before proceeding.
4. Variations in raw materials, application techniques, type of tile, substrate and environmental conditions can all limit colour consistency. For these reasons as with all manufacturers we cannot guarantee a consistent colour every time.

MIXING INSTRUCTIONS

1. Evo-Stik Technik TGS Grout should be added to water in a clean container whilst mechanically stirring and mixing thoroughly to give a smooth, consistent and easily worked mortar.
2. The recommended mixing proportions **by volume** are approximately 1 part water to 3 parts powder (not more than 1.7 litres per 5kg of powder).
3. Do not add more water than is necessary as this may prolong drying, modify colour shade and significantly reduce the compressive strength of the cured grout.
4. Part-used grout should never be “freshened up” with later water additions, but should always be discarded once it appears to lose workability.
5. In ideal conditions (20°C), Evo-Stik Technik TGS Grout will remain workable for up to 1 hour and then reach final set after about 24 hours.
6. Consolidate the joint with a rounded tool and wipe any excess grout away with a damp cloth. As the grout residues dry out, wipe again with a dry cloth to achieve a clean polished finish.
7. Do not apply any cement based coloured grout onto bare, un-sealed tiles without first checking that they will not be permanently stained and always ensure TGS grout residues are promptly and effectively removed as part of the application process.
8. When grouting over a large area using several bags of grout, ensure all mixes are from the same batch and that a consistent and identical water addition is used for each mix.
9. Any of the mix not used within its pot life should be discarded

APPLICATION

1. Pour the mixed grout onto the floor and work deeply into the joints using a spreader, squeegee or grouting trowel.
2. Work diagonally across the joints using a rubber squeegee to work the grout thoroughly and consistently into the tile joints, removing the excess as work proceeds across the tiled area.
3. Do not use excessive water to wash clean the tiled surface as fine grout residues can be washed off the tile face by wiping the surface with only a lightly damp cloth or sponge up to 2 hours after application, then a final clean & consistent finish can be achieved by using a dry cloth to evenly dry and polish the entire grouted area when the joints have begun to harden up.
4. Evo-Stik Technik TGS Grout will be extremely difficult to remove from tiled surfaces if left to dry.
5. If completing a shower, do NOT use shower for at least 2 weeks (BS 5385: Part 4:2009, clause 7.2.1).

STORAGE

Evo-Stik Technik TGS Grout is available in 5kg & 10kg bags and should be stored un-opened, clear of ground, in cool dry conditions. Protect from excessive draught and ideally used within 6 months.

CLEANING

1. Uncured product may be removed using cloths lightly dampened with water after carefully scraping off the bulk of the adhesive paste.
2. Cured product can only be removed by mechanical means.

PRECAUTIONS IN USE

For any application not covered please contact Technical Services on +353 1 8624998 or visit www.bostik.ie for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet, available at www.bostik.ie.

BOSTIK HOTLINE

Smart help +353 1 8624998



FM 01696
BS EN ISO 9001:2008

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top right hand corner on the front of this document.

Sales	Tel: 01 8624999	Fax: 01 8402186	orders.bostik-irl@bostik.com
Technical Advice	Tel: 01 8624998	Fax: 01 8402186	
Technical Data & COSHH (MSDS) Data Sheets	Tel: 01 8624900	Fax: 01 8402186	



FM 01696
BS EN ISO 9001:2008

Bostik Industries Ltd. Newtown, Swords, Co. Dublin. Ireland. Tel: +353 1 8624900 www.bostik.ie

DECLARATION OF PERFORMANCE

In accordance with Annex III of Regulation (EU) No 305/2011
(Construction Products Regulation)

Product Description:	EVO-STIK TECHNIK TGS GROUT
Product Barcode(s):	5099414561288, 5099414561387, 5099414561394, 5099414561400, 5099414561257, 5099414561356, 5099414561264, 5099414561363, 5099414400549, 5099414400327, 5099414561271, 5099414561370
Intended Use:	Improved cementitious grout with additional characteristics of reduced water absorption and high abrasion resistance
Manufacturer:	Bostik Industries Limited
Contact Address:	Newtown, Swords, Co. Dublin, Ireland Tel: 00 353 1 8624900 www.bostik.ie
System of Assessment:	System 3
Harmonised Standard:	BS EN 13888:2009
Notified Body:	1289

Essential Characteristics	Performance	Harmonised technical specification
Durability tested as: <ul style="list-style-type: none"> Abrasion resistance 	< 1000 mm ³	EN 12808-2
Compressive strength: <ul style="list-style-type: none"> After dry storage After freeze thaw cycles 	>15.0 N/mm ² >15.0 N/mm ²	EN 12808-3 EN 12808-3
Flexural strength: <ul style="list-style-type: none"> After dry storage After freeze thaw cycles 	> 2.5 N/mm ² > 2.5 N/mm ²	EN 12808-3 EN 12808-3
Water absorption: <ul style="list-style-type: none"> After 30 mins immersion After 6 hours immersion 	< 2.0g < 5.0g	EN 12808-5 EN 12808-5
Shrinkage:	< 3.0 mm/M	EN 12808-4
Reaction to Fire	NPD	
Release of dangerous substances	See MSDS	

This declaration of performance is issued under the sole responsibility of Bostik Ireland Ltd.

Signed for and on behalf of Bostik Ireland Ltd by:-

Name : Brian Monaghan

Signature: 

Date: May 2016



DECLARATION OF PERFORMANCE

In accordance with Annex III of Regulation (EU) No 305/2011
(Construction Products Regulation)